

**TURBO SEAL SERIES 75 WHITE
GENERAL PURPOSE THREAD SEALANT**

TURBO SEAL SERIES 75 is a high performance anaerobic thread sealant designed for the locking and sealing of metal threaded pipes and fittings with lubricating properties to facilitate proper assembly of torque tightening of piping components. It is ideal to seal against gases, water, LPG, hydrocarbons, oils and other chemicals and prevents pipe joints and fittings from loosening and leakage under vibration and shock.

Applications:

- General purpose thread sealant for a wide variety of industrial applications.
- Typical applications include, metal and fiber plants paper processing plants, chemical processing plants, waste treatment facilities, textile equipment and processing.

ADHESIVE PROPERTIES

Composition	Methacrylate ester
Appearance	White
Viscosity cP	90,500 cps (Brookfield RVT @ 25°C Spindle 3 @ 20 rpm)
Specific Gravity	1.17
Flash Point	> 100°C
Solvent Content	None

CURING PROPERTIES

Handling Cure Time	10 – 30 Minutes
Functional Cure Time	2 – 4 Hours
Full Cure Time	24 Hours
Breakaway Torque	1 N.m. 9 lb. in. (ISO 10964 M10 steel nuts and bolts)
Prevail Torque	1 N.m. 9 lb. in. (ISO 10964 M10 steel nuts and bolts)
Break Loose Torque	34 N.m. 300 lb. in. (Pre-Torqued to 5 N.m.) (ISO 10964 M10 steel nuts and bolts)
Max Prevail Torque	23.8 N.m. 210 lb. in. (Pre-Torqued to 5 N.m.) (ISO 10964 M10 steel nuts and bolts)
Compressive Shear Strength	> 1 N/mm ² 147 psi (ISO 10123 Steel Pins & Collars)
Temperature Range	-65°F to 300°F

PHYSICAL PROPERTIES

Coefficient of Thermal Expansion	80x10 ⁻⁶	ASTM D 696, K-1
Coefficient of Thermal Conductivity	0.10	ASTM C 177 W/(m.K)
Specific Heat	0.30	KJ/(kg.K)

CHEMICAL RESISTANCE

<u>Chemical</u>	<u>Temperature</u>	<u>% Initial Strength</u> <u>500 Hours</u>	<u>Retained</u> <u>1000 Hours</u>
Acetone	22°C	90	85
Ethanol	22°C	100	90
Motor Oil	125°C	100	100
Gasoline	22°C	100	95
Brake Fluid	22°C	100	90
Water/Glycol	87°C	100	90

Directions for Use:

Surfaces should be dry, clean and free of any contamination. Apply 360° bead of product to the leading threads of the male fitting, leaving the first thread free. Force the material into the threads and voids, adjust product amount accordingly and apply a 360° bead of product on the female threads also. Assemble and tighten as required.

Storage:

Anaerobic adhesives are ideally stored in a cool, dry place in unopened containers at room temperature, 46°F to 82°F. Do not return unused material to its original container.

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the Warranty: All products purchased from or supplied by Palm Labs Adhesives are subject to terms and conditions set out in the contract. Palm Labs Adhesives warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Palm Labs Adhesives is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Palm Labs Adhesives makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will nor infringe any patent.

Palm Labs Adhesives

10 Office Way, Hilton Head, SC 29928
Phone: 843 686-2345 Fax: 843 686-2230