

PALM LABS ADHESIVES
3063 Enterprise Road, DeBary FL, 32713
Phone (321) 710-4850 Fax (321) 710-4875
Email: Sales@PalmLabsAdhesives.com

TURBO FUSE FLUORESCENT YELLOW 100CP

Palm Lab's Cyanoacrylate is a one component rapid bonding adhesive. TURBO FUSE FLUORESCENT YELLOW advanced formula is designed to polymerize instantly by absorbing surface moisture. The product's performance has been tested with a variety of materials, and is recommended for a multitude of applications. It's Fluorescence allows it to be detected with a UV Light and the Yellow color is visible by the naked eye for secondary inspections. The fast curing qualities make it especially desirable in high speed industrial production.

Part Numbers for this TDS: 30-130FY

PHYSICAL PROPERTIES (Liquid State)

Base compound (Resin)	Ethyl Cyanoacrylate
Appearance	Yellow Liquid
Viscosity cP	180 - 220
Specific Gravity	1.05
Flash Point	170° F - 200° F (Tagliabue closed cup)
Shelf Life	1 Year
Soluble in Acetone, MEK, Amide, Methylene Chloride	

PHYSICAL PROPERTIES (Cured State)

Appearance	Clear-Hard
Softening Temperature (Fahrenheit)	300°F.
Service Temperature (Fahrenheit)	-65° to 180°F.
Hardness Barcol	65
Dielectric Constant at 1 MHz.	3.33
Specific Resistance	8.6 X 10 ² ohm/cm
Strength psi-Tensile Shear	2,500
Gap Fill	0.008 "

MATERIAL SET UP TIME

Aluminum to Aluminum	< 20 seconds
Steel to Steel	30 to 50 seconds
Phenolic to Phenolic	< 40 seconds
Polycarbonate to Polycarbonate	50 to 70 seconds
Rubber to Rubber	< 10 seconds

INFORMATION ON THIS PRODUCT AND OTHERS SUPPLIED TO USER IS BASED ON OUR GENERAL EXPERIENCE AND IS GIVEN IN GOOD FAITH, BUT BECAUSE OF THE MANY PARTICULAR FACTORS WHICH ARE OUTSIDE OF OUR KNOWLEDGE AND CONTROL AND AFFECT THE USE OF THE PRODUCT, NO WARRANTY IS GIVEN OR IMPLIED WITH RESPECT TO SUCH INFORMATION. FREEDOM UNDER PATENTS, COPYRIGHTS AND REGISTERED DESIGNS CANNOT BE ASSUMED.

Palm Labs Adhesives

Toll Free Phone 1-855-752-4583 Fax (321) 710-4875 Email: Sales@PalmLabsAdhesives.com 02/06/2017