

PALM LABS ADHESIVES
3063 Enterprise Road, DeBary FL, 32713
Phone (321) 710-4850 Fax (321) 710-4875
Email: Sales@PalmLabsAdhesives.com

TURBO FUSE SERIES 440SI – SURFACE INSENSITIVE (GEL)

Palm Lab's Cyanoacrylate is a one component rapid bonding adhesive. TURBO FUSE 440SI GEL SURFACE INSENSITIVE advanced thixotropic formula is designed to polymerize instantly by absorbing surface moisture. The product's performance has been tested with a variety of materials, and is recommended for a multitude of applications. The fast curing qualities make it especially desirable in high speed industrial production. TURBO FUSE SERIES 440SI GEL SURFACE INSENSITIVE is ideal for use in applications that require a gel like, viscous adhesive. It is also ideal for applications on vertical, angled or overhead surfaces. For extreme gap fill, the use of an accelerator is highly recommended.

Part Numbers for this TDS: 06-440SI, 07-440SI, 08-440SI, 09-440SI, S09-440SI, 35-440SI

PHYSICAL PROPERTIES (Liquid State)

Base compound (Resin)	Surface Insensitive Ethyl Cyanoacrylate
Appearance	Clear white gel
Viscosity cP	Not applicable – thixotropic gel
Specific Gravity	1.05
Flash Point	170° F - 200° F (Tagliabue closed cup)
Shelf Life	1 Year
Soluble in Acetone, MEK, Amide, Methylene Chloride	

PHYSICAL PROPERTIES (Cured State)

Appearance	Clear-Hard
Softening Temperature (Fahrenheit)	300°F.
Service Temperature (Fahrenheit)	-65° to 180°F.
Hardness Barcol	65
Dielectric Constant at 1 MHz.	3.33
Specific Resistance	8.6 X 10 ² ohm/cm
Strength psi-Tensile Shear	2,500
Gap Fill	0.010 "

MATERIAL SET UP TIME

Aluminum to Aluminum	20 to 30 seconds
Steel to Steel	50 to 100 seconds
Phenolic to Phenolic	< 90 seconds
Polycarbonate to Polycarbonate	50 to 70 seconds
Rubber to Rubber	10 to 25 seconds

Because of the thick gel consistency, it works especially well in poor fitting applications such as rough metal or ceramic repair, unfinished metal to metal bonding, and metal to rubber.

INFORMATION ON THIS PRODUCT AND OTHERS SUPPLIED TO USER IS BASED ON OUR GENERAL EXPERIENCE AND IS GIVEN IN GOOD FAITH, BUT BECAUSE OF THE MANY PARTICULAR FACTORS WHICH ARE OUTSIDE OF OUR KNOWLEDGE AND CONTROL AND AFFECT THE USE OF THE PRODUCT, NO WARRANTY IS GIVEN OR IMPLIED WITH RESPECT TO SUCH INFORMATION. FREEDOM UNDER PATENTS, COPYRIGHTS AND REGISTERED DESIGNS CANNOT BE ASSUMED.

Palm Labs Adhesives

Toll Free Phone 1-855-752-4583 Fax (321) 710-4875 Email: Sales@PalmLabsAdhesives.com

02/06/2017