

**PALM LABS ADHESIVES**  
3063 Enterprise Road, DeBary FL, 32713  
Phone (321) 710-4850 Fax (321) 710-4875  
Email: [Sales@PalmLabsAdhesives.com](mailto:Sales@PalmLabsAdhesives.com)

**TURBO SEAL - SERIES 76**  
**WHITE CONTROL STRENGTH - HIGH TEMPERATURE**  
**WITH PTFE THREAD SEALANT**

TURBO SEAL SERIES 76 is a high performance anaerobic thread sealant designed for the locking and sealing of metal threaded pipes and fittings with lubricating properties to facilitate proper assembly of torque tightening of piping components. It is ideal to seal against gases, water, LPG, hydrocarbons, oils and other chemicals and prevents pipe joints and fittings from loosening and leakage under vibration and shock.

**Part Numbers for this TDS:** 76-050, 76-300

Applications:

- General purpose thread sealant for a wide variety of pneumatic connections in industrial applications.
- Typical applications include, metal and fiber plants paper processing plants, chemical processing plants, waste treatment facilities, textile equipment and processing.

**ADHESIVE PROPERTIES**

Composition	Methacrylate ester
Appearance	White Paste
Viscosity cP	540,000 cps (Brookfield RVT @ 25°C Spindle 3 @ 20 rpm)
Specific Gravity	1.14
Flash Point	> 100°C
Solvent Content	None

**CURING PROPERTIES**

Handling Cure Time	10 – 30 Minutes
Functional Cure Time	2 – 4 Hours
Full Cure Time	24 Hours
Breakaway Torque	>1.7 N.m. >15 lb. in. (ISO 10964 M10 steel nuts and bolts)
Prevail Torque	1 N.m. 9 lb. in. (ISO 10964 M10 steel nuts and bolts)
Compressive Shear Strength	> 1 N/mm <sup>2</sup> 147 psi (ISO 10123 Steel Pins & Collars)
Temperature Range	-65°F to 400°F

### PHYSICAL PROPERTIES

Coefficient of Thermal Expansion	80x10 <sup>-6</sup>	ASTM D 696, K-1
Coefficient of Thermal Conductivity	0.10	ASTM C 177 W/(m.K)
Specific Heat	0.30	KJ/(kg.K)

### CHEMICAL RESISTANCE

<u>Chemical</u>	<u>Temperature</u>	<u>% Initial Strength</u> <u>500 Hours</u>	<u>Retained</u> <u>1000 Hours</u>
Acetone	22°C	70	60
Ethanol	22°C	90	90
Motor Oil	125°C	100	100
Gasoline	22°C	80	80
Brake Fluid	22°C	100	95
Water/Glycol	87°C	75	75

#### Directions for Use:

Surfaces should be dry, clean and free of any contamination. Apply 360° bead of product to the leading threads of the male fitting, leaving the first thread free. Force the material into the threads and voids, adjust product amount accordingly and apply a 360° bead of product on the female threads also. Assemble and tighten as required.

#### Storage:

Anaerobic adhesives are ideally stored in a cool, dry place in unopened containers at room temperature, 46°F to 82 °F. Do not return unused material to its original container.

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the Warranty: All products purchased from or supplied by Palm Labs Adhesives are subject to terms and conditions set out in the contract. Palm Labs Adhesives warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Palm Labs Adhesives is consider accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Palm Labs Adhesives makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will nor infringe any patent.

#### **Palm Labs Adhesives**

Toll Free Phone 1-855-752-4583 Fax (321) 710-4875 Email: [Sales@PalmLabsAdhesives.com](mailto:Sales@PalmLabsAdhesives.com)

02/06/2017